

# TECHNICAL DATA SHEET 产品说明书

GYMCOL ADHESIVES (PINGHU) Co., Ltd 2008 Xinqun Road, Economic Development Zone Pinghu, Zhejiang, China. www.gymcol.com.cn 金固牢胶粘剂 (平湖) 有限公司 中国浙江平湖经济开发区新群路 2008 号

Version 版本: 1

Edition 编辑: 2009-08-11

Page 页码 1/1

PRODUCT NAME 产品名称: XC-1000JC

**Description** 产品类型: Thermoplastic Solvent Based Adhesive 热塑型溶剂型胶粘剂

A thermoplastic solvent based adhesive that combine high performance with high solid content. Excellent toughness and permanent flexibility after cured. 热塑型高性能高固含溶剂胶。固化后具有极好的韧性和极好的弹性。

## MAIN APPLICATIONS 主要应用

This adhesive has fast drying and strong bonding, being indicated for applications with this requirement, thinking in faster production. In spite of being a solvent based adhesive, this adhesive has low smell. The best advantage of this formulation is the greater yield, because has very high solid content. 这是一款快干型,高强度的胶水,推荐它用于有要求干燥速度较快的产品上。这是一款具有很小气味的溶剂型胶水,最大的优点是含有很高的固含量。

Adhesive especially designed for bonding foam, foam with foam, wood, PE foam and difficult substrate with low surface energy. Ideal for PU foam repairs applications. This formula is recommended for sofa application and softly chair. 这个胶水适用于粘接海绵,海绵和海绵之间的粘接,木头,PE 泡沫以及具有低表面能的不同材料。尤其适用于 PU 海绵修补应用以及沙发和沙发椅的应用。

Solubility 可溶性

Non-polar solvents, such as toluene, hexane, etc 无极性的溶剂,例如甲苯,正己烷等等。

#### PRODUCT SPECIFICATIONS 产品指标

Property	Specifications
Color 颜色	Light yellow 浅黄色
Viscosity Brookfield, cp @ 25 °C, RV-2 粘度	200-400
Solid content, % 固含量	38-43
Density, g/cc 比重	0.78-0.83

<sup>\*</sup> Typical value 典型值

### APPLICATION INSTRUCTION 使用说明

The surface to be glue must be clean, free from dust, grease and moisture. It can be applied by brush; spatula, roll or pressure system. After the application must wait 2 minutes before bonding. Keep the union under pressure.首先清洁涂胶表面,除去干燥和油脂性物质或者灰尘。可以用刷子,抹刀以及滚转或压力系统来上胶。粘接前至少要等 2 分钟。并用力压紧。

#### STORAGE CONDITIONS 储存条件

This product contains volatile solvent. It is flammable. Keep in a well-ventilated place between  $5-35\,^\circ$  C. Keep away from sources of ignition. In this conditions the shelf life time is up to 8 months.这个产品含有挥发性溶剂,是易燃物。存放在  $5-35\,^\circ$  C 通风良好,远离火源的环境下保存时间是 8 个月。

Designed by:

José Ramón Cerezo Technical Director GSA

